

Product Data Sheet



Marble Chips 8-15 mm

is a pure crystalline lime of Ordovic-Silurian Age (about 400-500 million years). Dry Agriculture lime CaCO₃ (calcite) as dominant mineral. Dry Agricultural lime is a dry product (less than 0.5% water). The product is certified and manufactured according to. Aggregate for concrete: NS-EN 12620: 2002 + A1: 2008+NA: 2016.

Approved and registered
by Mattilsynet:
(Norwegian Food Safety
Authority)

- Acc. Drinking Water Regulations of 30 December 2016 No. 1372, §15.
approval date 21.06.2017

Product:

Marble Chips 8-15 mm

Declarable main components:

CaCO₃: min 98% CaCO₃ + MgCO₃: min 98.5%
NV (neutralizing value e. A.2.2): 98.5%
Acid-insolubility: 0.7%

Voluntarily declared components:

Calcium (Ca): 39%
Magnesium (Mg): less than 0.5%
Moisture: less than 0.5%

Findling Grad:
Percentilverdier
(supplier-
specific)

Declared	Tolerance
d90 = 14 mm	96-100% < 16 mm
d50 = 12 mm	45-65 % < 12 mm
d10 = 9 mm	2-8 % < 8 mm
	1% < 0.5 mm

Trace element:

Element	Typical values	Requirements NS-EN 1018 - Cleanest Product
Sb	< 0.90 mg/kg	≤ 3 mg/kg
As	< 0.90 mg/kg	≤ 3 mg/kg
Cd	< 0.09 mg/kg	≤ 2 mg/kg
Cr	< 2.4 mg/kg	≤ 10 mg/kg
Pb	< 0.6 mg/kg	≤ 15 mg/kg
Hg	< 0.001 mg/kg	≤ 0.5 mg/kg
Ni	< 2.3 mg/kg	≤ 10 mg/kg
Se	< 0.9 mg/kg	≤ 3 mg/kg

Density: 1.5-1.6 kg/dm³ (dry product)

Delivery method: In bulk (loose) - big bag (1000 kg) – pallets (25 kg x 42 bags)

Application: 8-15 mm is mainly used for aggregate for concrete, facade etc.

Storage: - Bulk goods: Indoor floor plan electricity. silo.

- Bags: Indoor / Outdoor. Make sure plastic / packaging is not damaged!

Safety precautions: Normally 8-15 mm does not form dust during handling - use if needed protective goggles and mask.



6493 LYGSTAD

Phone: +47 71299220

E-post: post@visneskalk.no

<http://www.visneskalk.no>